

# SpeedBlock AO1

Jun-2020 v.6

## Technical Data Sheet

### General Information


SpeedBlock AO1 is a highly efficient non discolouring sterically hindered phenolic antioxidant for use in polymer processing. SpeedBlock AO1 provides long term thermal stability at ppm addition levels and is typically used for polyolefin processing at 0.1 - 0.5%.

### Chemical Name

Tetrakis[methylene(3,5-di-tert-butyl-4-hydroxyhydro-cinnamate)]methane

CAS Number	EC Number	Mol. Wt.
6683-19-8	229-722-6	1177.6

### Structure



### Specification (LAM 316)

Appearance :	White powder
Assay :	≥ 98.0 %
Melting Point Range :	110.0 - 125.0 °C
Loss on Drying (%w/w, 60°C, 3 hours under vacuum) :	≤ 0.5 %w/w
Transmittance (UV SpectroPhotometer - 425nm) :	≥ 96.0 %
Transmittance (UV SpectroPhotometer - 500nm) :	≥ 98.0 %

### Applications

- Polyolefins
- Adhesives
- Polyurethanes
- Elastomers
- Styrene homo- and copolymers

### Storage and Handling

Stable for at least 2 year(s) at 20°C in a sealed container in the dark. A Safety Data Sheet is available on request.

### Transport Classification

(EUROPE AND USA) NON-HAZARDOUS

### Global Inventories

EINECS, TSCA, DSL, AICS, NZIoC, IECSC, CSCL, ECL, CSNN, PICCS

Disclaimer: Please consult Arkema's disclaimer regarding the use of our products on <https://www.arkema.com/en/products/product-safety/disclaimer/>

**LAMBSON**  
SPEEDBLOCK  
BY ARKEMA